

Product Data

NA 139

English	Generai information
Filtermaterial	Cellulose (90%) / Polyestor (10%)
Colour	white
Weight	120 g / m2
	0.07
Material Thickness	0.37 mm.
Airparmeability at 200 Pa.	43 CFM @ 0.6 WG
Temperature resistance	85 C
	Chemical Resistance
Oil and water resistance	Good
Hydrolysis resistance	Good
Acid resistance	Good
Alkalien resistance	Good
Dust release	Good
	Filtertest
	U,S,G
Application category after BIA	Prufzeugnis
	Nr.199823505/6210
Effenciency	97 % Parlikel

Application field

Fiitration of fine dust types in the metal working, mineral processing, shot blasting power coating and heavy varius dust